

Applic. No.: 10/686,849

Amdt. Dated July 29, 2005

Reply to Office action of May 12, 2005

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of claims:

Claim 1 (currently amended). A contact configuration, comprising:

a semiconductor body of semiconductor material in a monocrystalline phase;

a metalization layer; and

a layer of said semiconductor material in a substantially amorphous phase disposed between said semiconductor body and said metalization layer, for forming an ohmic contact between said metalization layer and said semiconductor body;

said semiconductor material being silicon and said layer being a layer of amorphous silicon doped with hydrogen.

Claims 2-4 (cancelled).

Claim 5 (currently amended). The contact configuration according to claim [[2]] 1, wherein said silicon semiconductor

Applic. No.: 10/686,849

Amdt. Dated July 29, 2005

Reply to Office action of May 12, 2005

body is n-conducting in a region of said layer of amorphous silicon.

Claims 6-7 (cancelled).

Claim 8 (currently amended). The contact configuration according to claim [[2]] 1, wherein said silicon semiconductor body is p-conducting in a region of said layer of amorphous silicon.

Claim 9 (original). The contact configuration according to claim 1, wherein said layer of amorphous semiconductor material has a thickness in the order of magnitude of nanometers.

Claim 10 (original). The contact configuration according to claim 9, wherein said thickness of said layer lies between 2 and 100 nm.

Claim 11 (original). The contact configuration according to claim 1, wherein said layer of amorphous semiconductor material has a doping of between 10^{15} and 10^{16} charge carriers per cm^3 .

Applic. No.: 10/686,849

Amdt. Dated July 29, 2005

Reply to Office action of May 12, 2005

Claim 12 (original). The contact configuration according to claim 1, wherein said metalization layer is formed of a metal selected from the group consisting of aluminum, chromium, and aluminum/chromium.

Claim 13 (original). The contact configuration according to claim 1, which comprises one of a trench component and a planar component formed in said semiconductor body.

Claim 14 (original). The contact configuration according to claim 13, wherein said component is selected from the group consisting of a diode, a bipolar transistor, a MOSFET, and an IGBT.

Claim 15 (original). The contact configuration according to claim 1, which comprises a field stop zone in said semiconductor body, said field stop zone adjoining said layer of said amorphous semiconductor material.

Claim 16 (original). The contact configuration according to claim 1, which further comprises an additional layer in said semiconductor body in a region of said layer of amorphous semiconductor material, said additional layer forming an emitter.

Applic. No.: 10/686,849

Amdt. Dated July 29, 2005

Reply to Office action of May 12, 2005

Claim 17 (original). The contact configuration according to claim 16, wherein said additional layer and said semiconductor body are of a common conductivity type.

Claim 18 (original). The contact configuration according to claim 16, wherein said additional layer and said semiconductor body having mutually opposite conductivity types.

Claim 19 (original). The contact configuration according to claim 16, wherein said additional layer is doped so weakly that, without said layer of amorphous semiconductor material, said additional layer forms one of a Schottky contact or an ohmic contact with a relatively high contact resistance.

Claim 20 (original). The contact configuration according to claim 1, wherein said layer of amorphous semiconductor material is formed on at least one of a front side and a rear side of said semiconductor body.

Claim 21 (original). The contact configuration according to claim 20, wherein said layer of amorphous semiconductor material is formed to locally attenuate an injection of charge carriers in critical component regions.

Applic. No.: 10/686,849

Amdt. Dated July 29, 2005

Reply to Office action of May 12, 2005

Claim 22 (original). The contact configuration according to claim 1, wherein said layer of amorphous semiconductor material is locally recrystallized.

Claim 23 (original). The contact configuration according to claim 1, wherein in said amorphous semiconductor material is silicon carbide.

Claim 24 (withdrawn - currently amended). A method for producing the contact configuration according to claim 1, which comprises:

providing a semiconductor body formed of silicon;

applying amorphous ~~semiconductor material~~ silicon doped with hydrogen on the semiconductor body by a process selected from the group consisting of sputtering, vapor deposition, and glow discharge; and

applying a metallization layer on the layer of amorphous silicon doped with hydrogen; and

subsequently subjecting the amorphous ~~semiconductor material~~ silicon doped with hydrogen to heat treatment and forming the contact configuration according to claim 1.

Applic. No.: 10/686,849

Amdt. Dated July 29, 2005

Reply to Office action of May 12, 2005

Claim 25 (withdrawn). The method according to claim 24, which comprises performing the heat treatment at about 350°C to 450°C.

Claim 26 (withdrawn). The method according to claim 24, which comprises sputtering in a hydrogen-containing atmosphere.

Claim 27 (withdrawn). The method according to claim 24, which comprises performing the heat treatment in a hydrogen-containing atmosphere.

Claim 28 (withdrawn). The method according to claim 24, which comprises locally recrystallizing the amorphous layer of silicon at temperatures above about 600°C in component regions.

Claim 29 (withdrawn - currently amended). A method for producing the contact configuration according to claim 1, which comprises:

providing a semiconductor body formed of silicon; and

forming an amorphous ~~semiconductor material~~ silicon in the semiconductor body by damage formation[[,]];

Applic. No.: 10/686,849

Amdt. Dated July 29, 2005

Reply to Office action of May 12, 2005

doping the amorphous silicon with hydrogen; and

applying a metallization layer on the layer of amorphous
silicon doped with hydrogen and producing the contact
configuration according to claim 1.

Claims 30-31 (cancelled).

Claim 32 (withdrawn - currently amended). The method
according to claim 29, which comprises introducing an
additional layer into the semiconductor body in a region of a
layer formed of amorphous ~~semiconductor material~~ silicon.

Claim 33 (withdrawn). The method according to claim 32,
wherein the additional layer is weakly doped.

Claim 34 (withdrawn). The method according to claim 29,
wherein the damage formation is effected by implantation.

Claim 35 (withdrawn). The method according to claim 34,
wherein the implantation comprises implanting elements of the
third period of the periodic table of elements.

Applic. No.: 10/686,849

Amdt. Dated July 29, 2005

Reply to Office action of May 12, 2005

Claim 36 (withdrawn). The method according to claim 34, which comprises implanting with an implantation dose of about $5 \cdot 10^{14}$ cm^{-2} to $1 \cdot 10^{16}$ cm^{-2} .

Claim 37 (withdrawn). The method according to claim 29, which comprises locally recrystallizing the amorphous layer of silicon at temperatures above about 600°C in component regions.